DIAION™ UBA120A

DIAION™ UBA120A is an anion exchange resin with a uniform particle size. It has a standard cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

		_1		_ 1	
$\mathbf{\nu}$	rn	α	11	CI	
	ıv	u	u	L	

Troduct					
Grade Name		DIAION TM UBA120A			
Туре	Strong Base Anion				
Matrix	Styrene-DVB, Gel				
Functional Group	Type I (trimethyl ammonium groups)				
lonic Form		Cl			
Specification					
Whole Bead Count	-	95 min.			
Salt Splitting Capacity	meq/mL	1.3 min.			
Water Content	%	49 - 55			
Mean Particle Size	μm	575 ± 50			
Uniformity Coefficient	-	1.2 max.			
Typical Properties					
Shipping Density	g/L	680			
Particle Density	g/mL	1.08			
Total Swelling (Cl to OH)	%	24			
Recommended Operating Conditions					
Maximum Operating Temperature	°C	80 (Cl ⁻)			
		60 (OH ⁻)			
Operating pH Range		0 - 14			
Minimum Bed Depth	mm	800			
Service Flow Rate	BV/h	10 - 60			
Regenerant		NaOH			
Regenerant Concentration	%	NaOH 2 - 8			
Regenerant Level	g/L	50 - 200			
Regenerant Flow Rate	BV/h	2 - 8			
Total Rinse Requirement	BV	2 - 10			

1 BV(Bed Volume)=1 m³/m³-resin

DIAION™ UBA120A

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAIONTM UBA120A resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBA120A




Fig. 2 Bed Expansion of UBA120A

DIAION™ UBA120A

Operational Capacity Data




Fig. 3 Operational Capacity Data of UBA120A Regenerant: 4 % NaOH

Notice

DIAIONTM is a registered trademark of Mitsubishi Chemical Corporation. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical Corporation specifications agreed to pursuant to a signed writing during the warranty period, and except as required by law, MITSUBISHI CHEMICAL CORPORATION AND ITS AFFLIATES MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.