

Product Data Sheet

DIAION™ AMP03

DIAION™ AMP03 is a gel type amphoteric resin. It has both weakly acidic cation and strongly basic anion functionality. It is recommended for ion retardation chromatography and applied to removal of salts from organic solutions.

Product

Grade Name	DIAION™ AMP03	
Type	Amphoteric Resin	
Matrix	Styrene-DVB, Gel	
Chemical Structure		
Functional Group	Quaternary Amine, Carboxylate	
Ionic Form	Inner Salt	

Specification

Whole Bead Count	-	95 min.
Total Exchange Capacity	meq/mL	0.75 min.
Salt Splitting Capacity	meq/mL	0.0015 max.
Water Content	%	49 - 55
Particle Size Distribution thr. 210 μm	%	1.0 max.
Particle Size Distribution 240 - 280 μm	%	85 min.

Typical Properties

Shipping Density	g/L	760
Mean Particle Size	μm	260
Particle Density	g/mL	1.09

Recommended Operating Conditions

Maximum Operating Temperature	°C	60
Effective pH Range		4 - 10
Minimum Bed Depth	mm	800
Service Flow Rate	BV/h	2 - 10
Regenerant		Water
Regenerant Flow Rate	BV/h	2 - 10
Total Rinse Requirement	BV	10 - 20

1 BV(Bed Volume)=1 m³/m³-resin

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ AMP03 resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of AMP03




Fig. 2 Bed Expansion of AMP03

Notice

DIAION™ is a registered trademark of Mitsubishi Chemical Corporation. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical Corporation specifications agreed to pursuant to a signed writing during the warranty period, and except as required by law, MITSUBISHI CHEMICAL CORPORATION AND ITS AFFILIATES MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.