

Product Data Sheet

DIAION™ SMN1

DIAION™ SMN1 is a nuclear grade mixed resin with strongly acidic cation exchange resin, DIAION™ SKN1, and strongly basic anion exchange resin, DIAION™ SAN1. It is used for cleanup system in primary circuit, cleanup system of SFP, radwaste, etc.

Product

Grade Name	DIAION™ SMN1	
Type	Mixed	
Matrix	Styrene-DVB, Gel	
Functional Group	Sulfonic acid / Type I (trimethyl ammonium groups)	
Ionic Form	H ⁺ / OH ⁻	
Chemical Equivalent Ratio	1 / 1	

Specification

Component		Cation Exchange Resin	Anion Exchange Resin
		DIAION™ SKN1	DIAION™ SAN1
Salt Splitting Capacity	meq/mL	1.7 min.	1.0 min.
Particle Size Distribution 425 - 1180 μm	%	95 min.	95 min.
Particle Size Distribution thr. 425 μm	%	1.0 max.	1.0 max.
Ionic Form Conversion H Form	eq%	99 min.	-
Ionic Form Conversion Na Form	eq%	0.1 max.	-
Ionic Form Conversion OH Form	eq%	-	90 min.
Ionic Form Conversion CO ₃ Form	eq%	-	10 max.
Ionic Form Conversion Cl Form	eq%	-	0.2 max.
Metal Content (Ca)	mg/L	50 max.	50 max.
Metal Content (Pb)	mg/L	10 max.	10 max.
Metal Content (Fe)	mg/L	50 max.	-
Metal Content (Cu)	mg/L	10 max.	-
Water Extractables	g/L	0.1 max.	0.1 max.

Typical Properties

Component	Mixed resin		
Shipping Density	g/L	720	
Component		Cation Exchange Resin	Anion Exchange Resin
		DIAION™ SKN1	DIAION™ SAN1
Mean Particle Size	μm	700	730
Particle Density	g/mL	1.20	1.07
Total Swelling (Na ⁺ to H ⁺)	%	9	-
Total Swelling (Cl ⁻ to OH ⁻)	%	-	23

Recommended Operating Conditions

Maximum Operating Temperature	°C	60
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	BV/h	10 - 60

1 BV(Bed Volume)=1 m³/m³-resin

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ SMN1 resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of SMN1

Notice

DIAION™ is a registered trademark of Mitsubishi Chemical Corporation. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical Corporation specifications agreed to pursuant to a signed writing during the warranty period, and except as required by law, MITSUBISHI CHEMICAL CORPORATION AND ITS AFFILIATES MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.