

Product Information

DIAION™ USMN3

DIAION™ USMN3 is a nuclear grade mixed resin with strongly acidic cation exchange resin, DIAION™ UBKN3, with ⁷Li form and strongly basic anion exchange resin, DIAION™ UBAN1. It is used for cleanup system in primary circuit of PWR nuclear power plants.

Product

Grade Name	DIAION™ USMN3		
Type	Mixed		
Matrix	Styrene-DVB, Gel		
Functional Group	Sulfonic acid / Type I (trimethyl ammonium groups)		
Ionic Form	⁷ Li ⁺ / OH ⁻		
Chemical Equivalent Ratio	1 / 1		

Specification

Component		Cation Exchange Resin		Anion Exchange Resin	
		DIAION™ UBKN3		DIAION™ UBAN1	
Salt Splitting Capacity	meq/mL	2.4 min.		1.1 min.	
Particle Size Distribution 425 - 1180 μm	%	95 min.		95 min.	
Particle Size Distribution thr. 425 μm	%	1.0 max.		1.0 max.	
Mean Particle Size	μm	600 - 730		580 - 680	
Ionic Form Conversion ⁷ Li Form	eq%	99 min.		-	
Ionic Form Conversion Na Form	eq%	0.1 max.		-	
Ionic Form Conversion OH Form	eq%	-		95 min.	
Ionic Form Conversion CO ₃ Form	eq%	-		5 max.	
Ionic Form Conversion Cl Form	eq%	-		0.2 max.	
Metal Content (Ca)	mg/L	50 max.		50 max.	
Metal Content (Pb)	mg/L	10 max.		10 max.	
Metal Content (Fe)	mg/L	50 max.		50 max.	
Metal Content (Cu)	mg/L	10 max.		10 max.	
Water Extractables	g/L-R	0.5 max.		0.1 max.	

Recommended Operating Conditions

Maximum Operating Temperature	°C	60
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	BV/h	10 - 60

1 BV(Bed Volume)=1 m³/m³-resin

Notice

DIAION™ is a registered trademark of Mitsubishi Chemical Corporation. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical Corporation specifications agreed to pursuant to a signed writing during the warranty period, and except as required by law, MITSUBISHI CHEMICAL CORPORATION AND ITS AFFILIATES MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

Mitsubishi Chemical Corporation

please visit <http://www.diaion.com/en>