

Product Data Sheet

DIAION™ CSK40H

DIAION™ CSK40H is a cation exchange resin with a uniform particle size. It has 14% cross-linkages and excellent properties. A wide range of applications, especially for condensate polishing in power plants, is recommended.

Product

Grade Name	DIAION™ CSK40H	
Type	Strong Acid Cation	
Matrix	Styrene-DVB, Gel	
Functional Group	Sulfonic acid	
Ionic Form	H ⁺	

Specification

Whole Bead Count	-	95 min.
Salt Splitting Capacity	meq/mL	2.4 min.
Water Content	%	33 - 43
Particle Size Distribution 500 - 850 μm	%	95 min.
Particle Size Distribution thr. 500 μm	%	1 max.
Mean Particle Size	μm	650 ± 50
Uniformity Coefficient	-	1.2 max.
Ionic Form Conversion H Form	eq%	99 min.
Ionic Form Conversion Na Form	eq%	0.1 max.

Typical Properties

Shipping Density	g/L	810
Particle Density	g/mL	1.27
Total Swelling (Na ⁺ to H ⁺)	%	5

Recommended Operating Conditions

Maximum Operating Temperature	°C	120
Operating pH Range		0 - 14
Minimum Bed Depth	mm	450
Service Flow Rate	m/h	Fast Rinse 5 - 60 Condensate Polishing 40 - 150
Regenerant		HCl H ₂ SO ₄
Regenerant Concentration	%	HCl 4 - 8 H ₂ SO ₄ 1 - 10
Regenerant Level	g/L	30 - 150
Regenerant Flow Rate	m/h	1 - 10
Total Rinse Requirement	BV	3 - 6

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ CSK40H resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of CSK40H




Fig. 2 Bed Expansion of CSK40H

Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.