

Product Data Sheet

DIAION™ UBK08H

DIAION™ UBK08H is a cation exchange resin with a uniform particle size. It has standard cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

Product

| | | |
|------------------|--------------------|--|
| Grade Name | DIAION™ UBK08H | |
| Type | Strong Acid Cation | |
| Matrix | Styrene-DVB, Gel | |
| Functional Group | Sulfonic acid | |
| Ionic Form | H ⁺ | |

Specification

| | | |
|---|--------|-----------|
| Whole Bead Count | - | 90 min. |
| Salt Splitting Capacity | meq/mL | 1.8 min. |
| Water Content | % | 50 - 56 |
| Mean Particle Size | μm | 620 ± 50 |
| Uniformity Coefficient | - | 1.10 max. |
| Ionic Form Conversion (H ⁺) | eq% | 95 min. |

Typical Properties

| | | |
|---|------|------|
| Shipping Density | g/L | 800 |
| Particle Density | g/mL | 1.20 |
| Total Swelling (Na ⁺ to H ⁺) | % | 9 |

Recommended Operating Conditions

| | | |
|-------------------------------|-----|--|
| Maximum Operating Temperature | °C | 120 |
| Operating pH Range | | 0 - 14 |
| Minimum Bed Depth | mm | 800 |
| Service Flow Rate | m/h | 10 - 40 |
| Regenerant | | HCl H ₂ SO ₄ |
| Regenerant Concentration | % | HCl 4 - 10 H ₂ SO ₄ 1 - 4 |
| Regenerant Level | g/L | 30 - 150 |
| Regenerant Flow Rate | m/h | 2 - 10 |
| Total Rinse Requirement | BV | 2 - 10 |

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ UBK08H resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBK08H




Fig. 2 Bed Expansion of UBK08H

Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.