

## Product Data Sheet

## DIAION™ PA306S

DIAION™ PA306S is a small particle porous type strongly basic anion exchange resin. It has a 3% cross-linkages and excellent properties. A wide range of applications, especially in a field of industrial chromatographic separation.

## Product

Grade Name	DIAION™ PA306S	
Type	Strong Base Anion	
Matrix	Styrene-DVB, Porous	
Functional Group	Type I (trimethyl ammonium groups)	
Ionic Form	Cl <sup>-</sup>	

## Specification

Whole Bead Count	-	95 min.
Salt Splitting Capacity	meq/mL	0.8 min.
Water Content	%	66 - 76
Particle Size Distribution on 425 μm	%	14 max.
Particle Size Distribution thr. 150 μm	%	1 max.

## Typical Properties

Shipping Density	g/L	720
Mean Particle Size	μm	310
Effective Size	mm	0.23
Uniformity Coefficient	-	1.4
Particle Density	g/mL	1.04
Total Swelling (Cl <sup>-</sup> to OH <sup>-</sup> )	%	23

## Recommended Operating Conditions

Maximum Operating Temperature	°C	80 (Cl <sup>-</sup> ) 60 (OH <sup>-</sup> )
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 60
Regenerant		NaOH
Regenerant Concentration	%	NaOH 2 - 8
Regenerant Level	g/L	50 - 200
Regenerant Flow Rate	m/h	2 - 8
Total Rinse Requirement	BV	2 - 10

### Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ PA306S resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of PA306S

### Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.