Product Data Sheet

DIAION™ HP2MGL

DIAION™ HP2MGL is based on crosslinked methacrylate. It does not contain any aromatic compounds. It is considered an intermediate polarity adsorbent resin. It is recommended for desalting and adsorption of organic compounds of relatively high polarity by using the more hydrophilic character of the polymer matrix.

Product

Grade Name	DIAION™ HP2MGL
Type	Synthetic Adsorbents
Matrix	Methacrylic, Porous

Specification

Whole Bead Count	-	95 min.
Water Content	%	55 - 65
Particle Size Distribution thr. 355 µm	%	1 max.
Effective Size	mm	0.40 min.
Uniformity Coefficient	-	1.6 max.

Properties

Shipping Density	g/L	725
Mean Particle Size	µm	570
Particle Density	g/mL	1.09
Specific Surface Area	m2/g	570
Pore Volume	mL/g	1.3
Pore Radius	Å	240

Recommended Operating Conditions

Maximum Operating Temperature	°C	130
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Flow rate	BV/h	Loading 0.5 - 5
	BV/h	Displacement 0.5 - 2
	BV/h	Regeneration 0.5 - 2
	BV/h	Rinse 1 - 5
Regenerant		Organic solvents for hydrophobic compounds
		Bases for acidic compounds
		Acids for basic compounds
		Buffer solution for pH sensitive compounds
		Water for an ionic solution
		Hot steam for volatile compounds

1 BV(Bed Volume)=1 m^3/m^3-resin

Product Data Sheet

DIAION™ HP2MGL

Pore Size Distribution



Fig. 1 Pore size distribution of HP2MGL

Swelling Ratio In Various Solvents

Methanol	1.02
Ethanol	1.05
2-Propanol	1.02
Acetone	1.04
Toluene	1.07
Acetonitrile	1.01
Water	1.00

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ HP2MGL resin in normal down flow operation is shown in the graph below.



Fig. 2 Pressure Drop of HP2MGL

Product Data Sheet

DIAION™ HP2MGL

Indicative Applications

- Purification of small peptides, oligonucleotides and proteins
- Adsorption of vitamins, antibiotics, enzymes, steroids and other substance from fermentation solutions
- Decolorization of various sugar solutions
- Adsorption of fatty acids
- Adsorption of various perfume
- Decolorization and purification of various chemicals

FDA Status

DIAION™ HP2MGL may be used to process food and beverage products and isolate specialized food additives as intended. Such use may be said to fully comply with the Federal Food, Drug, and Cosmetic Act, and applicable food additive regulations, including 21 CFR 177.2420 (Polyester resins, cross-linked).

Storage condition

Synthetic adsorbents are recommended to store properly in order to avoid a high risk for mold growth. The proper storage typically allows any synthetic adsorbent resin to last for a year after production before onset of any such growth.
The best storage condition is with 20% of alcohol such as ethanol or isopropanol. A 10% or higher concentration of salt solution, such as NaCl, is also recommended to preserve new or used resin for long storage.
In case salt cannot be used, a 0.01 to 0.02 N of NaOH solution could be accepted as mold cannot withstand survival at pH higher than 12.
Storage at freezing temperature should be avoided at all cost as it may cause breakage or crush of resin particles.

Notice

DIAION™ is a registered trademark of Mitsubishi Chemical Corporation. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical Corporation specifications agreed to pursuant to a signed writing during the warranty period, and except as required by law, MITSUBISHI CHEMICAL CORPORATION AND ITS AFFLIATES MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.