

Product Data Sheet

SEPABEADS™ SP70

SEPABEADS™ SP70 is highly porous styrenic adsorbents. It has moderate surface area and a narrower pore size distribution than DIAION™ HP20. It can be adapted to the US FDA standard, 21 CFR 173.65 and used for various food application.

Product

Grade Name	SEPABEADS™ SP70
Type	Synthetic Adsorbent
Matrix	Ethylvinylbenzene-DVB, Porous

Specification

Whole Bead Count	-	95 min.
Water content	%	57 - 67
Particle Size Distribution thr. 250 µm	%	5 max.
Effective size	mm	0.25 min.
Uniformity Coefficient	-	1.6 max.
Specific Surface Area	m ² /g	700 min.
DVB extractables	ppb	50 max.

Properties

Shipping Density	g/L	690
Particle Density	g/mL	1.01
Pore Volume	mL/g	1.5
Pore Radius	Å	70

Recommended Operating Conditions

Maximum Operating Temperature	°C	130
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Flow rate	BV/h	Loading 0.5 - 5
	BV/h	Displacement 0.5 - 2
	BV/h	Regeneration 0.5 - 2
	BV/h	Rinse 1 - 5
Regenerant		
	Organic solvents for hydrophobic compounds	
	Bases for acidic compounds	
	Acids for basic compounds	
	Buffer solution for pH sensitive compounds	
	Water for an ionic solution	
	Hot steam for volatile compounds	
1 BV(Bed Volume)=1 m ³ /m ³ -resin		

Pore size distribution




Fig. 1 Pore size distribution of SP70

Swelling Ratio In Various Solvents

Methanol	1.15
Ethanol	1.21
2-Propanol	1.11
Acetone	1.21
Toluene	1.20
Acetonitrile	1.18
Water	1.00

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of SEPABEADS™ SP70 resin in normal down flow operation is shown in the graphs below.




Fig. 2 Pressure Drop of SP70

Indicative Applications

- Purification of juices
- Removal of naringin and other bittering agents
- Purification of small peptides, oligonucleotides and proteins
- Adsorption of vitamins, antibiotics, enzymes, steroids and other substance from fermentation solutions
- Decolorization and purification of various chemicals

FDA status

SEPABEADS™ SP70 may be used to process food and beverage products and isolate specialized food additives as intended. Such use may be said to fully comply with the Federal Food, Drug, and Cosmetic Act, and applicable food additive regulations, including 21 CFR 173.65 (Divinylbenzene copolymer).

Storage condition

Synthetic adsorbents are at high risk of mold growth. Accordingly, synthetic adsorbents should be stored properly. Properly stored synthetic adsorbent resins may be stored for up to one year after production before the onset of any mold growth is detected. Optimal storage is with a 20% alcohol solution such as ethanol or isopropanol. A 10% or higher concentration of salt solution, such as NaCl, is also recommended to preserve new or used resin for storage. In case salt cannot be used, a 0.01 to 0.02 N NaOH solution may be acceptable as mold cannot withstand survival at pH higher than 12. Storage at freezing temperatures should be avoided as it may cause breakage or crush certain resin particles.

Notice

SEPABEADS™ is a registered trademark of Mitsubishi Chemical Corporation. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical Corporation specifications agreed to pursuant to a signed writing during the warranty period, and except as required by law, MITSUBISHI CHEMICAL CORPORATION AND ITS AFFILIATES MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.